

TECHNICAL DATA SHEET

QM-DA-55-026

Gültig ab: 29.10.2014

Revision: 8

Product description

Grade:

Vicell® 6722 / 60 DS

PROPERTY	EDANA METHODE	TOLERANCES			UNIT
		Min	Target	Max	
Basis weight	WSP 130.1	57	60	63	g/m ²
Thickness 1-ply	WSP 120.6	0,76	0,80	0,84	mm
Thickness 1-ply after winder	WSP 120.6	0,73	0,78	0,81	mm
Tensile strength dry MD CD	Option B WSP 110.4	15,00	25,0	30,00	N/5cm
		9,00	15,0	22,50	N/5cm
Elongation dry MD CD	Option B WSP 110.4	6,00	12,00	20,00	%
		5,00	14,00	18,00	%
Tensile strength wet MD CD	Option B WSP 110.4	7,50	11,00	14,50	N/5cm
		5,00	7,00	9,00	N/5cm
Liquid Absorbency Capacity	WSP 10.01	7	8,5	12	g/g
		420	510	720	g/m ²
Liquid strike through time	WSP 70.3	0	2	4	s

This is not a specification.

Properties are given as typical average values off-machine with tolerances of +/-3 sigma.

"Please be advised that it is the responsibility of the finished good producer to ensure that their product meets all applicable regulations and that it is suitable for use in the intended application.

Other than the product data listed above, GP does not make any representations or warranties as to the performance of its rolled good products or their suitability for use in a given finished good application."



Wir sind zertifiziert nach DIN EN ISO 9001.